

TA-Steel

Galvalume | DX51 D+AZ 185 SLV

Product Datasheet

Designations

DIN EN 10215/10143

Chemical composition

	C (%)	Mn (%)	S (%)	Si (%)	Al (%)	Nb (%)	Ti (%)
DX51D + AZ	≤ 0.180	≤ 1.200	≤ 0.045	≤ 0.50	-	-	≤ 0.300

Physical features

Edge protection	Industrial environments	Adhesion to fold	Hardness on the cross section
Very good	0.30 µm/Year	1 T	140 HV 100 HV for HFX grade

Surface protection

Salt spray test, resistance to corrosion (ISO 7253/DIN 50021)	50 hours/µm
Outdoor exposure, resistance to corrosion (marine environment)	0.60 µm/year

Heat transfer	Resistance to the Tmax temperature	Fire resistance
65 Watts/m ²	315°C	According to European Standards (EN 13501-1) A1

Mechanische Eigenschaften | Mechanical features

Thickness (mm)	Re (MPa)	Rm	A80 (%)	Bending ratio (th)	Tensile strength R _m	Elongation at break
0.2 – 0.5	-	270- 500	≥ 18	-	270 - 500	22
0.5 – 0.7			≥ 20			
0.7 – 2.00			≥ 22			

02 | 10.2025

The Best Part

Tacke + Lindemann GmbH

Beratgerstraße 31-33 | 44149 Dortmund

Tel +49 (0)231 17 77 7-0
 Fax +49 (0)231 17 77 7-50
 E-Mail info@tacke-lindemann.de
 Web www.tacke-lindemann.de

Disclaimer

Our products are based on careful research and reflect the current state of the art. The data and information are provided to the best of our knowledge, but without guarantee. All values given are average values, not maximum or minimum values, and do not constitute a guarantee. Changes and deviations are possible; we expressly reserve the right to make technical adjustments.

It is the responsibility of the user to independently check the suitability of the product for the respective application before use.

We accept no liability for errors, inaccuracies, omissions or changes. Furthermore, the applicable regulations, rules and DIN standards must be observed.

The use of texts, images and drawings, even in part, is not permitted without consent.

Our General Terms and Conditions (GTC) apply exclusively.